

	Blast Furnace air-cooled slag							
Sieves	0/6	0/20	6/20	0/60	20/60	60/120	Grave ROLAC	
180.0 mm						100.0%		
125.0 mm						88.0%		
100.0 mm								
80.0 mm				100.0%	100.0%	62.0%		
63.0 mm				100.0%	100.0%	11.5%		
50.0 mm				96.0%	84.0%			
40.0 mm		100.0%	100.0%	88.0%	65.0%	5.0%		
31.5 mm		100.0%		78.0%	40.0%			
28.0 mm		98.7%	100.0%	73.0%	15.0%			
20.0 mm		95.2%	96.0%	66.0%	6.0%			
16.0 mm		82.5%	74.0%	59.0%	3.0%			
14.0 mm		75.5%	59.0%					
12.5 mm		70.7%	47.0%					
10.0 mm	100.0%	64.0%	30.0%	47.0%				
8.0 mm	98.0%	58.8%	16.0%	42.0%				
6.3 mm	94.0%	54.2%	5.0%					
5.0 mm	88.0%	49.8%	4.0%	26.0%				
4.0 mm	80.0%	45.3%	2.0%	25.0%				
3.15 mm	73.0%	42.6%	2.0%	23.0%				
2.5 mm								
2.0 mm	62.0%	37.2%		21.0%				
1.60 mm								
1.25 mm								
1.0 mm	44.0%	28.2%		17.0%				
800 µm								
630 µm								
500 µm		25.5%						
400 µm								
315 µm								
250 µm								
200 µm	15.0%	7.0%	2.0%	3.0%				
160 µm								
125 µm								
100 µm								
80 µm	5.9%							
63 µm	3.8%	4.3%	1.9%	1.2%				