

Phoenix Services France - VALLOUREC & LME sites at St-Saulve

Sieves	EAF furnace slag							
	GNT 0/20	GNT 0/40	GNT 0/150					
200 mm			100.0%					
150 mm			87.0%					
100.0 mm								
80.0 mm			81.0%					
63.0 mm		100.0%	81.0%					
50.0 mm								
40.0 mm		98.0%	68.0%					
31.5 mm	100.0%	95.0%	62.0%					
28.0 mm								
20.0 mm	98.0%	87.0%	54.0%					
16.0 mm	94.0%	82.0%	51.0%					
14.0 mm	90.0%	80.0%	50.0%					
12.5 mm	85.0%	76.0%	47.0%					
10.0 mm	76.0%	70.0%	43.0%					
8.0 mm	65.0%	63.0%	37.0%					
6.3 mm	53.0%	54.0%	32.0%					
5.0 mm								
4.0 mm	33.0%	39.0%	23.0%					
3.15 mm								
2.5 mm								
2.0 mm	16.0%	23.0%	13.0%					
1.60 mm								
1.25 mm								
1.0 mm	8.0%	11.0%	7.0%					
800 µm								
630 µm								
500 µm	5.0%	6.0%	4.0%					
400 µm								
315 µm								
250 µm	3.0%	4.0%	3.0%					
200 µm								
160 µm								
125 µm	3.0%	3.0%	2.0%					
100 µm								
80 µm								
63 µm	1.9%	1.8%	1.3%					