

| | Blast Furnace air-cooled slag | | | | | | | |
|----------|-------------------------------|-----------------|-----------------|-----------------|------------------|------------------|--------|--------|
| Sieves | LT 0006 0/6 | LT 0020 0/20 | LT 0620 6/20 | RE 0040 0/40 | LT 2040 20/40 | LT 0100 0/100 | GTL00 | G2LR00 |
| 150.0 mm | | | | | | 100.0% | | |
| 100.0 mm | | | | | | 96.4% | | |
| 80.0 mm | | | | | 100.0% | | | |
| 63.0 mm | | | | | 100.0% | 73.3% | | |
| 50.0 mm | | | | 100.0% | 100.0% | 66.7% | | |
| 40.0 mm | | 100.0% | 100.0% | 100.0% | 99.7% | 61.0% | | |
| 31.5 mm | | 100.0% | | 97.8% | 79.6% | | 100.0% | 100.0% |
| 28.0 mm | | 100.0% | 100.0% | | 56.3% | | | |
| 20.0 mm | | 97.2% | 93.7% | 85.1% | 11.0% | 44.3% | 96.3% | 95.9% |
| 16.0 mm | | 88.6% | | | 7.1% | | | |
| 14.0 mm | | | 61.7% | | | | | |
| 12.5 mm | 100.0% | 78.0% | | | 3.3% | | | |
| 10.0 mm | 100.0% | 69.2% | | 62.2% | 1.9% | 24.7% | 71.2% | |
| 8.0 mm | | | | | | | | |
| 6.3 mm | 91.6% | 54.4% | 4.2% | | | | 59.7% | 56.6% |
| 5.0 mm | | 48.9% | | 46.3% | | 15.6% | | |
| 4.0 mm | | 43.5% | | | | 14.7% | 51.3% | |
| 3.15 mm | 66.1% | | 2.9% | | | | | |
| 2.5 mm | | 35.9% | | | | | | |
| 2.0 mm | | 32.2% | | 36.3% | | 11.1% | 41.6% | 33.4% |
| 1.60 mm | | | | | | 10.1% | | |
| 1.25 mm | | 26.3% | | | | | | |
| 1.0 mm | | 23.3% | | 28.5% | | 8.3% | | |
| 800 µm | | | | | | 7.4% | | |
| 630 µm | | | | | | 6.6% | | |
| 500 µm | | 16.6% | | 20.6% | | | 18.1% | 17.6% |
| 400 µm | | 14.9% | | | | 5.1% | | |
| 315 µm | | 13.1% | | | | 4.4% | | |
| 250 µm | | | | 14.3% | | | | 12.3% |
| 200 µm | | 10.2% | | | | 3.2% | 8.9% | |
| 160 µm | | 9.0% | | | | 2.7% | | 10.0% |
| 125 µm | | 7.8% | | 6.1% | | 2.2% | | |
| 100 µm | | 6.8% | | 5.4% | | 1.9% | | |
| 80 µm | | 5.7% | | 4.7% | | 1.6% | 4.8% | 7.0% |
| 63 µm | 2.8% | 4.7% | | 4.0% | | 1.3% | 4.1% | 6.1% |